

MAXIMUS

HERRINGBONE CLICK 55

Fischgrät Click - Bâton Rompu Click - Visgraat Click



INVICTUS

Technical Specification - Technische Spezifikationen - Spécifications techniques - Technische specificaties

Description - Beschreibung - Description - Omschrijving	Rigid core SPC with click locking system	
Thickness - Gesamtdicke - Epaisseur - Dikte	EN ISO 24337	5.00 mm
Wearlayer - Nuttschicht - Couche d'usure - Slijtlaag	EN ISO 24340	0.55 mm
Wearlayer PUR coating - Schutz vor Schmutz PUR - Traitement polyurethane - PUR slijtlaag behandeling		Scratchmaster® top layer
Weight per sqm - Flächengewicht g/m ² - Poids total g/m ² - Totaal gewicht g/m ²	EN ISO 23997	ca. 9700 g/m ²
Locking System - Verschlussystem - Système de verrouillage - Vergrendelingsysteem		Unilin's Unizip® click technology
Classification - Eignungsklasse - Classe d'usage - Gebruiksklasse	EN ISO 10874	33 Commercial Heavy - 42 Industrial General



Performance - Leistungen - Prestaties

Reaction to fire - Brandverhalten - Classement feu - Brandklasse	EN 13501-1	Bfl-S1
Slip resistance - Rutschfest - Glissance - Antislip	EN 13893	DS
Slip restraint (dynamic coefficient of friction) - Rutschhemmung - Résistance au glissement - Slipweerstand	DIN 51130	R10
Thermal conductivity - Wärmeleitfähigkeit - Conductivité thermique - Warmtegeleiding	EN 12664	0.165 (W/m.K)
Thermal resistance R value - Wärmedurchlasswiderstand R - Résistance thermique R - Wamtedoorlaatweerstand R	EN 12664	0.031 (m ² .K)/W
Underfloor heating - Bodenheizung - Chauffage par le sol - Vloerverwarming	EN ISO 12524	Yes, max. 27°C
Electrostatic performance - Antistatik - Accumulation de charges électrostatiques - Electrostatische propensiteit	EN 1815	< 2 kV
Residual indentation - Eindrückverhalten - Poinçonnement rémanent - Restindruk	EN ISO 24343-1	< 0.1 mm
Dimensional stability - Massänderung - Stabilité dimensionnelle - Dimensionele stabiliteit	EN ISO 23999	≤ 0.15%
Curling - Schüsselung - Incurvation - Krulling	EN ISO 23999	pass
Castor chair resistance - Stuhlrollenfestigkeit - Résistance aux chaises à roulettes - Bestand tegen stoelwielen	EN 425	pass, Type W
Colour fastness - Farbechtheit - Solidité de la couleur - Kleurechtheid	EN ISO 105-B02	> 6
Impact sound insulation - Trittschallverbesserungsmaß - Efficacité acoustique - Kontaktgeluidisolatie	EN ISO 717-2	8dB (ΔLw) / 17dB with FIRMO underlay
Chemical / Stain resistance - Fleckenbeständigkeit - Résistance aux taches - Vlekbestendigheid	EN ISO 26987	pass
Abrasion resistance - Verschleißfestigkeit - Résistance à l'abrasion - Slijtvastheid	EN ISO 660-1	class T
Indoor AIR quality - French VOC regulation	ISO 16000	Greenguard GOLD - Floorscore - A+
Content of pentachlorophenol		PCP under detection limit
Formaldehyde emissions (28 days test)	EN ISO 717-1	NA HCHO (has not been added)
Phthalate free		Yes, biobased
CE marking	EN 14041:2011	

Packaging - Verpackung - Emballage - Verpakking

Size and packaging	EN ISO 24342	145x743 mm
Size and packaging / carton	EN ISO 24342	14 planks / carton = 1.509 m ² / carton
Packages / pallet	EN ISO 24342	56 cartons/pallet

Warranty - Garantie

Warranty - Garantie 25 years Residential - 15 years Commercial

The technical data is correct at the time of printing. - 04/2023

